



255 Wooster Road North • Barberton, Ohio 44203  
Phone: (330) 745-9016 • Fax: (330) 745-4886  
www.tahomarubberplastics.com

## **BALED FRICTION**

### **Typical Composition**

30-40% Tire Cord  
70-60% Tire Friction Compound NR/SBR  
Productive (Curatives incorporated)  
Does not contain wire

### **Typical Form**

Approximately 45 lb per Bale  
Approximate Bale Size: 4 x 15 x 30 inches  
Standard Cord Length is 1.25 Inch  
Optional P-1502 is Rubber enriched with 0.5-inch cord length

### **Typical Use**

Incorporate: High abrasion resistance  
Elevated Heat Resistance  
Good Low Temperature Resistance  
High Tear Strength

Can be milled into blanks on a standard "Cracker" Mill or incorporated into rubber recipes to achieve a balance of above (or desired customer properties)

### **Typical Cured Properties**

Specific Gravity: 1.16 ± .05  
Shore A Durometer: 75-85  
Tensile Strength: +1000 PSI

### **Samples**

Available upon request

The Technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risks of use, storage and handling of product. **No warranty, express or implied, is made including, but not limited to, implied warranties of merchantability and fitness for a particular purpose.** Nothing contained herein shall be construed as a license to operate under, or recommended to infringe, any patents.